

HAF 4S

LOW DENSITY GASKET MATERIAL

General properties and application :

HAF 4S : It is designed for various oil, air and coolant applications such as oil pans, front covers, intake manifolds and rear seals. Offers improved oil sealability over nitrile butadiene bound materials . Max Operating temperature 290°C

Technical Data

Physical Properties	Unit	Typical Value
Density	gm/cc	1.44 min
Compressibility at 350 kg/cm ²	%	9-23
Recovery (Min)	%	45
Tensile Strength (Min)	kg/cm ²	86

Fluid absorption

Weight Increase			
ASTM Oil No. 3	5 Hrs @ 150°C (Max)	%	-
ASTM Fuel B	5 Hrs @ 21 to 30°C (Max)	%	-
Water Distilled	5 Hrs @ 21 to 30°C (Max)	%	-

Thickness Increase			
ASTM Oil No. 3	5 Hrs @ 150°C (Max)	%	-
ASTM Fuel B	5 Hrs @ 21 to 30°C (Max)	%	-
Water Distilled	5 Hrs @ 21 to 30°C (Max)	%	-

Availability	Unit	Standard Size
Thickness range	mm	0.50 -1.00 in Rolls
	mm	above 1.00 -1.50 in sheets
Roll width	mm	1000 ± 20
Roll Weight	Kgs	50
Sheet Size	mm	1000 x 1000

All information data quoted are based on experience in production of sealing elements. However, In view of the wide variety of possible installation and operating conditions one can not draw final conclusions in all application cases regarding the behaviors in a gasket joint.

Whenever there is any doubt, our staff will be pleasure to assist you in finding the optimum sealing solutions.