

## HAF 9082

LOW DENSITY GASKET MATERIAL

### General properties and application :

**HAF 9082** : It is mix of reinforced fibers with high rubber contents. It is a flexible material with high recovery property and can be used for soft gasket applications like oil/fuel/water pumps, carburetors, gearboxes, oil pans etc. Max Operating temperature 180°C

### Technical Data

Specification values determined in accordance with ASTM F-104 Type 7

Physical Properties	Unit	Typical Value
Density	gm/cc	1.20 (Min)
Compressibility at 350 kg/cm <sup>2</sup>	%	15-30
Recovery (Min)	%	35
Tensile Strength (Min)	kg/cm <sup>2</sup>	110

### Fluid absorption

#### Weight Increase

ASTM Oil No. 3	5 Hrs @ 150°C (Max)	%	40
ASTM Fuel B	5 Hrs @ 21 to 30°C (Max)	%	40
Water Distilled	5 Hrs @ 21 to 30°C (Max)	%	40

#### Thickness Increase

ASTM Oil No. 3	5 Hrs @ 150°C (Max)	%	20
ASTM Fuel B	5 Hrs @ 21 to 30°C (Max)	%	20
Water Distilled	5 Hrs @ 21 to 30°C (Max)	%	20

Availability	Unit	Standard Size
Thickness range	mm	0.40 -1.50 in Rolls
Roll width	mm	1000 ± 20
Roll Weight	Kgs	50

All information data quoted are based on experience in production of sealing elements. However, In view of the wide variety of possible installation and operating conditions one can not draw final conclusions in all application cases regarding the behaviors in a gasket joint.

Whenever there is any doubt, our staff will be pleasure to assist you in finding the optimum sealing solutions.