

General properties and application :

HAF 9316 : It is fully cured styrene butadiene rubber binder and a blend of Aramid and cellulose fibers. It is intended for oil and water application. Max Operating temperature 290°C

Technical Data

Specification values determined in accordance with ASTM F-104 Type 7

Physical Properties	Unit	Typical Value
Density	gm/cc	1.44 min
Compressibility at 350 kg/cm²	%	15-25
Recovery (Min)	%	40
Tensile Strength (Min)	kg/cm²	100

Fluid absorption

Weight Increase				
ASTM Oil No. 3	5 Hrs @ 150ºC (Max)	%	-	
ASTM Fuel B	5 Hrs @ 21 to 30ºC (Max)	%	-	
Water Distilled	5 Hrs @ 21 to 30ºC (Max)	%	-	

Thickness Increase				
ASTM Oil No. 3	5 Hrs @ 150ºC (Max)	%	25-65	
ASTM Fuel B	5 Hrs @ 21 to 30ºC (Max)	%	10-40	
Water Distilled	5 Hrs @ 21 to 30ºC (Max)	%	-	

All information data quoted are based on experience in production of sealing elements. However, In view of the wide variety of possible installation and operating conditions one can not draw final conclusions in all application cases regarding the behaviors in a gasket joint.

Whenever there is any doubt, our staff will be pleasure to assist you in finding the optimum sealing solutions.